

| |
|---------|
| Water |
| Oil |
| Solvent |

Product information

Product Description An uncoated paper for line drawings and check prints with simple fills

Physical Properties

| | | | |
|----------------------------|---------------------|-----------------------------|--------------------|
| Grammage | 75 g/m ² | Acidity | PH 7,5 ± 1 |
| Thickness | 102 µm | Whiteness CIE | 159 |
| Reflection R457 +UV | 109 % | Reflection R457 - UV | 83 % |
| Opacity | 92 % | Stiffness MD | 140 mN |
| Stiffness CD | 55 mN | Porosity | 820 ml/min |
| Roughness WS | 240 ml/min | Roughness TS | 260 ml/min |
| Moisture content | 4,9 % | L*: a*: b* | 94,1 : 3,5 : -16,4 |

Storage Conditions Best results are obtained between 20 ± 3°C and 50 ± 5 % RH.

Available Widths (mm)

| | | | | | | | | |
|----------------|--------|--------|--------|--------|--------|-------------|---------|------|
| 2" core | 297 mm | 420 mm | 594 mm | 610 mm | 625 mm | 841 mm | 914 mm | 1067 |
| Length | 120 m | 120 m | 120 m | 50 m | 50 m | 50/91/120 m | 50/91 m | 50m |

Storage Conditions Best results are obtained between 20 ± 3°C and 50 ± 5 % RH.

Printer Compatibility

Please refer to mediaguide.oce.com

Lamination Compatibility

| Hot | Warm | Cold | |
|-----|------|------|--------------------------------------|
| 1 | 1 | 3 | Hot, heat activated: 105 °C – 130 °C |
| | | | Warm, heat activated: 85 °C – 95 °C |
| | | | Cold, pressure sensitive |

3 = excellent 2 = fair 1 = not recommended

Outdoor Use Designed for indoor use.

Colour Profiles Océ develops high-quality colour profiles for media / ink / toner / printer / RIP combinations. Check availability of profiles for your printer on the download section of www.mediaguide.oce.com.



“From sustainably managed forests – For more info: www.pefc.org”